

GOTECH "the best partner" to raise your competition

GT-7012-A AKRON耐磨試驗機 Akron Abrasion Tester

BS-903、GB/T 1689、JIS-K6264

本機適用於硫化橡膠及彈性材料耐磨性能測試。通過量測試樣與砂輪摩擦後之磨耗體積，判定其耐磨性能。可設定磨耗轉數，到達設定轉數並自動停機。

This tester is designed to use together with a special balance for testing the abrasive consumption for the rubber products such as tire, belt of tank, ...etc.



磨耗砂輪 Grinding Wheel	直徑為150mm·厚度25mm·中心孔直徑32mm·粒度為36號；磨料為氧化鋁 Outside dia Φ150mm·25mm(w)·grit 36#
砂輪軸轉速 Grinding wheel rotating speed	34±1 r.p.m.
膠輪軸轉速 Specimen Rotating speed	BS 903 : 250±5 r.p.m. JIS K6264 : 75±5 RPM 或 250±5 r.p.m.(擇一) GB/T 1689 : 76±2 r.p.m.
試驗荷重 Load	26.7±0.2 N
試樣傾斜角度範圍 Specimen Slanted Range	0°~35° 可調 adjustable
計數器 Counter	LCD 液晶顯示 0~99,999,999次 可設定
體積 Dimension (W×D×H)	57×52×45 cm
重量(約) Weight (approx.)	60 kg
電源 Power	1φ AC 220V (依國別或指定 or specify)

瞭解更多產品信息，請登錄我司網站 www.gotech.biz