

GOTECH "the best partner" to raise your competition

GT-FSM01 快速塑性計 Rapid Plastimeter

ISO 2007、BS ISO 2007、ASTM D3194、JIS K6300-3、GB/T 3510

快速塑性計採用觸控式螢幕技術，操作簡便直觀，同時配備了高精度的測量系統，確保測試結果的準確性和可靠性。該設備不僅適用於測試天然生膠和未硫化膠的塑性（P0），還適用於測量天然生膠的塑性保持率（PRI），滿足多種測試需求。

The GT-FSM01 is specifically designed for measuring the plasticity (P0) of raw and unvulcanized rubber. It is also suitable for determining the plasticity retention index (PRI). Integrated with an HMI touchscreen and a high-precision measuring system, this tester ensures accurate and reliable test results.



溫度 Test temperature	100°C
預熱時間 Preheat time	15s
測試時間 Test time	15s
預載入荷重 Preload	300N
測試荷重 Test load	100N
上壓盤 Upper platen	φ7.3mm±0.02mm、φ10mm±0.02mm、φ14mm±0.02mm
體積(約) (W×D×H) Dimensions (approx.)	37 cm × 36 cm × 56.5cm
電源 Power	1φ AC 220V 50Hz (依國別或指定 or specify)

瞭解更多產品資訊，請登錄我司網站 www.gotech.biz